

TECHNICAL DESCRIPTION SHEET

DIAMOND P+60

ESI00925

PRODUCT CHARACTERISTICS

Pile Height	60mm	(+/- 2mm)
Total Length of Tuft Pile	126mm	(+/- 4mm)
Gauge	3/4 - 5/8	
Production Method (DIN 61151)	TUFTED	
Stitch Rate Per m2 approx	8,150	(+/- 5%)
Filaments Per m2 approx	97,800	(+/- 5%)
Total Weight	2.365 gr/m2	(+/- 1mm)
Perforation Diameter	5mm	
Number of Perforations	90 nr/m2	
Water Permeability (EN12616-Requirements>360L/H)	>360 l/h	

YARN CHARACTERISTICS

Decitex	13,600 dtex 100% Polyethylene	(+/- 8%)
Composition	360 microns	
Thickness	Straight monofilament	(+/- 5%)
Type	Bicolour (Light & Dark Green)	
Colour	1.450 gr/m2	
Total Yarn Weight		(+/- 5%)

YARN CHARACTERISTICS

Primary Backing	100% Polypropylene 215 gr/m2	
Primary Backing Weight	Two-Component	(+/- 8%)
Coating	Polyurethane	
Coating Weight	700 gr/m2	(+/- 10%)

The technical specifications and the quantities of the infill material to be used for the configuration of the system must comply with the certificates of the single national and/or international Federations or can be requested from us.