

TECHNICAL DESCRIPTION SHEET

ZIDA TEAKWOOD

PROPERTIES	TESTING METHODS	RESULTS
Wood Material		Teakwood
Shock Absorption	EN 14808:2005	45 % (-4% / +2%)
Vertical Deformation	EN 14809:2005	1.7mm (-0.1mm / 0.2mm)
Friction (slip/skid resistance)	EN 13036-4:2011 (CEN rubber, dry)	95
Vertical ball behaviour	EN 12235:2013 (Basketball)	92% (-2% / +3%)
Resistance to a rolling load	EN 1569:2020	0.15mm No Excessive Damage
Resistance to wear	ISO 5470-1:2016 CS 10& 500g 1000 Cycles	78 mg